



Received: 07-05-2026  
Accepted: 17-06-2026

ISSN: 2583-049X

## **Comparative Study of Surface Roughness in Turning of C45 Steel under Dry, Flood, and Coconut Oil-Based MQL Conditions**

<sup>1</sup> Van-Manh Ngo, <sup>2</sup> Thi-Bich-Ha Pham

<sup>1,2</sup> Thai Nguyen University of Technology, Vietnam

DOI: <https://doi.org/10.62225/2583049X.2026.6.3.6541>

Corresponding Author: Van-Manh Ngo

### **Abstract**

This study investigates the influence of cooling–lubrication conditions on surface roughness in turning of C45 steel. Experiments were conducted on an EMCO Maxxturn 45 CNC lathe using carbide cutting tools. The cutting parameters were fixed at a cutting speed of 160 m/min, a feed rate of 0.15 mm/rev, and a depth of cut of 1.0 mm. Three machining conditions, namely dry cutting, flood cooling, and coconut oil-based minimum quantity lubrication (MQL), were compared. The results showed that

dry cutting produced the highest surface roughness (2.25  $\mu\text{m}$ ), while flood cooling and MQL reduced the roughness to 1.26  $\mu\text{m}$  and 1.31  $\mu\text{m}$ , respectively. Compared with dry cutting, flood cooling and MQL decreased surface roughness by 44.0% and 41.8%, respectively. The findings indicate that coconut oil-based MQL can provide surface quality comparable to conventional flood cooling while offering a more sustainable machining approach.

**Keywords:** C45 Steel, Surface Roughness, Turning, MQL, Coconut Oil, Flood Cooling

### **1. Introduction**

Surface roughness is one of the most important indicators of machined surface quality because it directly affects the functional performance, wear resistance, and fatigue life of engineering components. In turning operations, surface roughness is influenced by several factors, including cutting parameters, tool geometry, workpiece material, and cooling–lubrication conditions. Among these factors, the cooling–lubrication method plays a significant role in controlling friction and heat generation in the cutting zone, thereby affecting the integrity of the machined surface [1, 2, 3].

Conventional flood cooling has been widely employed in machining processes due to its ability to dissipate heat and improve tool life. However, the excessive use of cutting fluids may cause environmental pollution, health problems for machine operators, and high costs associated with fluid maintenance and disposal [4, 5]. Dry machining has therefore attracted considerable attention as an environmentally friendly alternative. Nevertheless, the absence of lubrication often results in increased cutting temperature, severe tool wear, and deterioration of surface quality, especially under high-speed cutting conditions [6, 7, 8].

Minimum quantity lubrication (MQL) has emerged as a sustainable machining technique capable of reducing cutting fluid consumption while maintaining adequate lubrication at the tool–chip interface. Vegetable oils are considered suitable lubricants for MQL applications because of their biodegradability, renewability, and excellent lubricating properties. Among them, coconut oil possesses high oxidative stability and good viscosity characteristics, making it a promising candidate for machining applications [9, 10, 11]. Several studies have reported that vegetable oil-based MQL systems can effectively improve machining performance and surface finish compared with dry cutting [5, 12, 13, 14, 15].

Although numerous investigations have been conducted on vegetable oil-based MQL, limited information is available regarding the application of coconut oil in turning C45 steel. Therefore, the present study aims to compare the surface roughness obtained under three cooling–lubrication conditions, namely dry cutting, conventional flood cooling, and coconut oil-based MQL. Experiments were performed under identical cutting parameters to evaluate the effectiveness of coconut oil-based MQL as a sustainable alternative to conventional flood cooling.

### **2. Experimental Procedure**

The experiments were carried out on an EMCO Maxxturn 45 CNC lathe under controlled laboratory conditions. The

workpiece material used in this study was C45 steel with a diameter of 40 mm and an average hardness of approximately 200 HB. Carbide cutting tools were employed for all turning operations to ensure stable cutting performance. Three cooling–lubrication conditions, namely dry cutting, conventional flood cooling, and coconut oil-based minimum quantity lubrication (MQL), were investigated. In the MQL condition, coconut oil was supplied to the cutting zone in the form of an oil mist. The cutting parameters were kept constant throughout the experiments at a cutting speed of 160 m/min, a feed rate of 0.15 mm/rev, and a depth of cut of 1.0 mm. Surface roughness ( $R_a$ ) was measured using a surface roughness tester, and the average value was recorded for each machining condition.

**Table 1:** Cutting parameters used in the experiments

Parameter	Value
Cutting speed, $V_c$ (m/min)	160
Feed rate, $f$ (mm/rev)	0.15
Depth of cut, $a_p$ (mm)	1
Workpiece material	C45 steel (200 HB)
Tool material	Carbide
Cooling-lubrication conditions	Dry, Flood, MQL

### 3. Results and Discussion

The surface roughness values obtained under different cooling–lubrication conditions are presented in Table 2.

**Table 2:** Surface roughness under different cooling-lubrication conditions

Condition	$R_a$ ( $\mu\text{m}$ )
Dry cutting	2.25
Flood cooling	1.26
Coconut oil-based MQL	1.31

Dry cutting resulted in the highest surface roughness value of 2.25  $\mu\text{m}$ . The application of flood cooling and coconut oil-based MQL significantly improved the surface finish, reducing the roughness to 1.26  $\mu\text{m}$  and 1.31  $\mu\text{m}$ , respectively. Compared with dry cutting, flood cooling and MQL decreased surface roughness by approximately 44.0% and 41.8%, respectively.

The superior performance of flood cooling can be attributed to its better cooling capability, which effectively dissipates heat generated during machining. Although coconut oil-based MQL produced a slightly higher roughness than flood cooling, its performance was comparable while consuming a much smaller amount of lubricant. Therefore, coconut oil-based MQL can be considered a promising and environmentally friendly alternative to conventional flood cooling in turning operations.

### 4. Conclusions

This study compared the effect of dry cutting, flood cooling, and coconut oil-based MQL on the surface roughness in turning of C45 steel. The results showed that dry cutting produced the highest surface roughness, whereas flood cooling achieved the lowest value of 1.26  $\mu\text{m}$ . Coconut oil-based MQL yielded a comparable roughness value of 1.31  $\mu\text{m}$  and reduced surface roughness by approximately 41.8% compared with dry cutting. These findings suggest that coconut oil-based MQL has the potential to replace

conventional flood cooling in sustainable machining applications.

### 5. Acknowledgment

The author gratefully acknowledges the support provided by Thai Nguyen University of Technology.

### 6. References

- Do T-V, Hsu Q-C. Optimization of minimum quantity lubricant conditions and cutting parameters in hard milling of AISI H13 steel. *Applied Sciences*. 2016; 6(3):p. 83.
- Nguyen H-T, Hsu Q-C. Study on cutting forces and material removal rate in hard milling of SKD 61 alloy steel. *J. Chin. Soc. Mech. Eng.* 2017; 38(1):41-51.
- Davim JP. *Machining of hard materials*. Springer Science & Business Media, 2011.
- Do TV, Phan TD. Multi-objective optimization of surface roughness and MRR in milling of hardened SKD 11 steel under nanofluid MQL condition. *International Journal of Mechanical Engineering and Robotics Research*. 2021; 10:357-362.
- Astakhov VP. Metal cutting theory foundations of near-dry (MQL) machining. *IJMMM*. 2010; 7(1-2):p. 1. Doi: 10.1504/IJMMM.2010.029843
- Das RK, Sahoo AK, Mishra PC, Kumar R, Panda A. Comparative machinability performance of heat treated 4340 Steel under dry and minimum quantity lubrication surroundings. *Procedia Manufacturing*. 2018; 20:377-385.
- Phan T-D, Do T-V, Pham T-L, Duong H-L. Optimization of cutting parameters and nanoparticle concentration in hard milling for surface roughness of JIS SKD61 steel using linear regression and taguchi method. In *Advances in Engineering Research and Application: Proceedings of the International Conference on Engineering Research and Applications, ICERA 2020*, Springer, 2021, 628-635.
- Tran TH, *et al.* Improvement of wheel life by optimization of dressing parameters in surface grinding of SKD11 steel. In *Materials Science Forum*, Trans Tech Publ, 2021, 68-74.
- Boubekri N, Shaikh V. Minimum quantity lubrication (MQL) in machining: Benefits and drawbacks. *J Ind Intell Inf.* 2015; 3(3). Accessed: Mar. 19, 2025. [Online]. Available: <https://www.academia.edu/download/81201941/d97f17b193ee5ead8846aedf3e8ef633d25a.pdf>
- Dhar NR, Islam MW, Islam S, Mithu MAH. The influence of minimum quantity of lubrication (MQL) on cutting temperature, chip and dimensional accuracy in turning AISI-1040 steel. *Journal of Materials Processing Technology*. 2006; 171(1):93-99.
- Nguyen Q-M, Nguyen H-T, Le N-A-V, Nguyen T-N, Dang T-H-T, Do T-V. Investigation on the effect of nanofluid-MQL parameters on surface roughness during milling of hardened 9CrSi steel. In *Proceedings of the 2<sup>nd</sup> Annual International Conference on Material, Machines and Methods for Sustainable Development (MMMS2020)*, Springer, 2021, 311-316.
- Do TV. Empirical model for surface roughness in hard milling of AISI H13 steel under nanofluid-MQL condition based on analysis of cutting parameters.

- Journal of Mechanical Engineering Research and Developments. 2020; 43(2):89-94.
13. Vu MH, Hue PTM, Huynh NT, Nguyen QM. Multi-objective Optimization for Enhanced Material Removal Rate and Reduced Machining Roughness in Hard Turning of SKD61 Alloy Steel. *Mathematical Modelling of Engineering Problems*. 2024; 11(3).
  14. Günan F, Kıvık T, Yıldırım ÇV, Sarıkaya M. Performance evaluation of MQL with AL<sub>2</sub>O<sub>3</sub> mixed nanofluids prepared at different concentrations in milling of Hastelloy C276 alloy. *Journal of Materials Research and Technology*. 2020; 9(5):10386-10400.
  15. Hong TT, *et al.* Multi-objective optimization of surface roughness and MRR in surface grinding of hardened SKD11 using grey-based Taguchi method. In *Advances in Engineering Research and Application: Proceedings of the International Conference on Engineering Research and Applications, ICERA 2020*, Springer, 2021, 584-593.